

PRODUCT DATA SHEET

Purolite™ MB400

polistyrenowy żelowy, żelowy, złożo mieszane, forma wodorowa, forma wodorotlenowa

GŁÓWNE ZASTOSOWANIA

- demineralizacja - złoża mieszane
- kartridże

ZALETY

- ogólne zastosowanie

SYSTEMY

- system regenerowany współprądowo
- przeciwprądowy system regenerowalny
- złożo mieszane
- Working Mixed Bed

ZGODNOŚĆ Z REGULACJAMI

- certyfikowany IFANCA Halal

DOSTĘPNOŚĆ OPAKOWAŃ

- worek 1 ft³
- worki 25 litrów
- beczka (kartonowa) 6 ft³

PODSTAWOWE WŁAŚCIWOŚCI FIZYCZNE I CHEMICZNE:

Wygląd	kuliste ziarna	
zawartość wilgoci (max.)	65 %	
zakres wielkości ziaren	300 - 1200 µm	
< 300 µm (max.)	1 %	
współczynnik jednorodności (max.)	1.7	
ciężar nasypowy (średnio)	705 - 740 g/L (44.1 - 46.2 lb/ft ³)	
limit temperatury, złożo nie regenerowalne	100 °C (212.0 °F)	
limit temperatury, złożo regenerowalne	60 °C (140.0 °F)	
nazwa składnika	żelowy kationit silnie kwaśny	żelowy anionit silnie zasadowy typu I
struktura polimeru	żelowy polistyren sieciowany dwuwinylobenzenem	żelowy polistyren sieciowany dwuwinylobenzenem
grupa funkcyjna	kwas sulfonowy	czwartorzędowa amoniowa typu I
forma jonowa	forma H ⁺	forma OH ⁻
kationit/anionit proporcje objętościowe	40 %	60 %

Ecolab is a global developer, manufacturer, and supplier of Purolite™ Resins including ion exchange, catalyst adsorbent and advanced polymers that make the world cleaner and healthier.

www.puoliteresins.com



We're ready to solve your process challenges.

For further information on products and services, visit www.puoliteresins.com or complete a Contact Us form via PuoliteResins.com/contact-us or use the QR code.

Contact Us Form:



The statements, technical information and recommendations contained herein are believed to be accurate as of the date hereof. Since the conditions and methods of use of the product and of the information referred to herein are beyond our control, Purolite expressly disclaims any and all liability as to any results obtained or arising from any use of the product or reliance on such information; NO WARRANTY OF FITNESS FOR ANY PARTICULAR PURPOSE, WARRANTY OF MERCHANTABILITY OR ANY OTHER WARRANTY, EXPRESSED OR IMPLIED, IS MADE CONCERNING THE GOODS DESCRIBED OR THE INFORMATION PROVIDED HEREIN. The information provided herein relates only to the specific product designated and may not be applicable when such product is used in combination with other materials or in any process. Nothing contained herein constitutes a license to practice under any patent and it should not be construed as an inducement to infringe any patent and the user is advised to take appropriate steps to be sure that any proposed use of the product will not result in patent infringement.

