

Purolite™ UltraClean™ UCW9966

polistyrenowy żelowy, żelowy, złożo
mieszane, forma wodorowa, forma
wodorotlenowa, nie separowalne,
uziarnienie dla wody ultra czystej

GŁÓWNE ZASTOSOWANIA

- woda ultra czysta

ZGODNOŚĆ Z REGULACJAMI

- certyfikowany IFANCA Halal

DOSTĘPNOŚĆ OPAKOWAŃ

- karton 1 CF
- beczki 50 litrów
- beczka (kartonowa) 6 ft³

PODSTAWOWE WŁAŚCIWOŚCI FIZYCZNE I CHEMICZNE:

Wygląd	kuliste ziarna	
TOC (max.)	< 1 ppb TOC po 100 OZ płukania przy przepływie 30 OZ/h (*)	
oporność	> 18 MΩ cm w przeciągu 2 OZ z przepływem 30 BV/h (*)	
ciężar nasypowy (średnio)	670 - 710 g/L (41.9 - 44.4 lb/ft³)	
limit temperatury	60 °C (140.0 °F)	
nazwa składnika	żelowa kationitowa o uziarnieniu do wody ultra czystej	żelowa anionitowa typu I o uziarnieniu do wody ultra czystej
struktura polimeru	żelowy polistyren sieciowany dwuwinylobenzenem	żelowy polistyren sieciowany dwuwinylobenzenem
grupa funkcyjna	kwasy sulfonowe	czwartorzędowa amoniowa typu I
forma jonowa	forma H ⁺	forma OH ⁻
kationit/anionit proporcje ekwiwalentów chemicznych	1	1
całkowita pojemność (min.)	1.9 val/L (forma H ⁺)	1.0 val/L (forma OH ⁻)
konwersja (min.)	99.9 % (forma H ⁺)	95 % (forma OH ⁻)
zawartość wilgoci	49 - 54 % (forma H ⁺)	52 - 58 % (forma Cl ⁻)
przypis	* Jakość wody płucznej : > 17.5 MΩ cm; < 2 ppb TOC	

Ecolab is a global developer, manufacturer, and supplier of Purolite™ Resins including ion exchange, catalyst adsorbent and advanced polymers that make the world cleaner and healthier.

www.puoliteresins.com



We're ready to solve your process challenges.

For further information on products and services, visit www.puoliteresins.com or complete a Contact Us form via PuoliteResins.com/contact-us or use the QR code.

Contact Us Form:



The statements, technical information and recommendations contained herein are believed to be accurate as of the date hereof. Since the conditions and methods of use of the product and of the information referred to herein are beyond our control, Purolite expressly disclaims any and all liability as to any results obtained or arising from any use of the product or reliance on such information; NO WARRANTY OF FITNESS FOR ANY PARTICULAR PURPOSE, WARRANTY OF MERCHANTABILITY OR ANY OTHER WARRANTY, EXPRESSED OR IMPLIED, IS MADE CONCERNING THE GOODS DESCRIBED OR THE INFORMATION PROVIDED HEREIN. The information provided herein relates only to the specific product designated and may not be applicable when such product is used in combination with other materials or in any process. Nothing contained herein constitutes a license to practice under any patent and it should not be construed as an inducement to infringe any patent and the user is advised to take appropriate steps to be sure that any proposed use of the product will not result in patent infringement.